

SEALCOAT D41

Highly Penetrative Bituminous primer

Description

Sealcoat D41 is a solvent based cold applied, highly penetrative thin bituminous solution in black color.

Uses

- For priming concrete, masonry, metal and asphalt surfaces.
- Suitable for use as priming coat before applying any bituminous coating, or modified bitumen membrane in roofing, dam proofing, and waterproofing below or above ground level.

Surface Preparation

Surface must be clean, free from dirt, dust, oil and grease. New concrete must be fully cured, and dried before priming.



Standard

SEALCOAT D41 complies with the requirements of JS 674-90 and ASTM D 41: 05 Type I.

Coverage

It covers from 0.3 to 0.5 Kg./sm (0.2 – 0.4 kg/sm) depending on application method, surface properties and condition of substrates.

Dry time

It dries to touch in 2-4 hours. But time needed to complete dry is from 12 to 24 hours dependent on prevailing conditions.

Technical Data

PROPERTIES	RESULTS	TEST METHOD
Color	Black	-
Viscosity Saybolt @ 25 OC.	25 – 125 sec	ASTM D 88
Specific gravity @ 25 OC.	0.958	ASTM D 1475
Solubility in trichloro ethylene	99.7%	ASTM D 2042
Distillation volume @ 225 °C	37%	ASTM D -402
Distillation volume @ 360 °C	42.5%	ASTM D -402
Asphalt residue @225 oC	63%	ASTM D -402
Asphalt residue @360 oC	57.5%	ASTM D -402
Penetration @25 oC for Asphalt residue @360 oC	< 50 dmm	ASTM D - 5
Water Content. %	<0.5	ASTM D95
Flash Point.	45 OC	ASTM D 94
Drying time through.	8 - 12-Hours	In house
Coverage rate.	0.3 - 0.5 kg./mt2	In house
Shelf life	2-years	In house

Application temperature

It can be applied at a temperature between 2°C and 50°C.

Application

The primer is applied on a single coat. It should be well scrubbed in by brush, ensuring only a thin coating is applied or applied thinly but evenly by spray.

Containers

SEALCOAT D41 can be supplied in 15-kg., pail and 180-Kg., drum.

Storage

Store in tightly closed containers under cover and away from sources of heat and ignition.

SEALCOAT D41

Highly Penetrative Bituminous primer

Safety Precautions

- Use only with proper ventilation.
- Avoid contact skin and eyes by careful working.
- Do not use near open flame.
- It is advisable to use goggles and gloves.
- In case of eye contact immediately wash with cold water or consult the physician

Technical Support

International Insulation Company (IIC) – Bitugulf technical support team consist of expert engineers on the filed offers a comprehensive service support to specifiers, end users and contractors and on-site technical assistance.



INTERNATIONAL INSULATION COMPANY (BITUGULF)

Factory

Western Shuaiba Industrial, Block (3), Building (90),
Opposite of Kuwait Steel Co.

Telephone: (+965) 23262822

Fax: (+965) 23262825

Email: info@knimco.com

Showroom

Shuwaikh Industrial, Block (A), Building (139),
Opposite to Hyundai Maintenance Center

Telephone: (+965) 24912765, 90019917

Fax: (+965) 24912776

Email: shwrm@knimco.com

Website: www.knimco.com